TECHNICAL SPECIFICATIONS

Level III+ AR550 ARMOR



STAND ALONE MULTI-CURVE BALLISTIC INSERT

NIJ-STD-0101.06 Level III + Special Threats

SHOOTERS CUT - HARD ARMOR -TORSO PANEL MULTI-CURVE

THINNESS: .6" (15.24 mm) WITH POLYSHIELD ANTI-SPALL COATING

| PART NUMBER | WIDTH x LENGTH | WEIGHT |
|-----------------|-------------------------|--------------------|
| AR550-1012-SPC | 10 x12 254 x 305 mm | 8.5 lb 3.855 kg |
| AR550-0810-SPC | 8 x 10 203 x 254mm | 5.4 lb |
| AR550-1114-SPC | 11 x 14 279 x 356 mm | 9.7 lb |
| AR550-1012S-SPC | 10 x12 254 x 305 mm | 9.5 lb 4.309 kg |





MANUFACTURING TOLERANCES SPC PLATES:

Thickness dimensions are +-1/16 in. Width and length dimensions are +0.00 to 0.25 in. All weights are +-5% on SPC plates.

THREAT PERFORMANCE MATRIX



| 7.62 x 51mm M80 BALL - FMJ | 2,780 ft/s 847.34 m/s |
|----------------------------|--------------------------|
| 7.62 x 39mm 120.5 gr* | 2,380 ft/s 725.42 m/s |
| 5.56 x 45mm XM193 BT | 3,150 ft/s 960.12 m/s |
| 5.56 x 45mm M855 BT* | 3,115 ft/s 975.36 m/s |

*NIJ 0101.07 DRAFT LEVEL RF2 THREAT

CALIBER ARMOR BALLISTIC RESISTANCE TESTING PROTOCOL:

All testing was conducted on an indoor range at ambient conditions, in accordance with our instructions and the modified provisions of:

NJ-**STD-0101.06, Level III.** Testing was conducted using caliber $.7.62 \times 51$ mm, M80 Ball, 149 grain ammunition. The test sample was positioned 25 feet from the muzzle of the barrel to produce zero (0°) obliquity impacts. Photoelectric infrared screens were located at 10.20 feet and 15.53 feet which, in conjunction with electronic chronographs, were used to compute bullet velocities at 12.86 feet forward of the muzzle. The striking velocity was computed using standard drag formulas. Penetrations are determined by visual examination of the 5.5-inch-thick clay backing material witness plate. Back-face signature was measured using a calibrated digital depth gauge.

MJ-STD-0101.07 DRAFT, RF2. Testing was conducted using caliber 7.62 X 39mm Surrogate, 123 grain, 5.56mm, M855 BT, 62 grain, 7.62 X 51mm, M80 Ball, 149 grain, and 5.56mm, M193, 56 grain ammunition. The test samples were positioned 25 feet from the muzzle of the barrel to produce zero (0°) degree obliquity impacts. Photoelectric infrared screens were located at 10.20 feet and 15.53 feet which, in conjunction with electronic chronographs, were used to compute bullet velocities at 12.86 feet forward of the muzzle. The striking velocity was computed using standard drag formulas. Penetrations are determined by visual examination of the 5.5-inch-thick clay backing material. Back-face signature was measured using a calibrated digital depth gauge.

GENERAL INFORMATION

Caliber Armor AR550 Body Armor design made with AR550 ballistic steel. Multi-shot rated. Finished with either a standard coating to avoid corrosion or PolyShield Advanced Anti-Spall Protective Coating . Made in the U.S.A, Louisville, KY



Caliber Armor, LLC - 1421 Selinda Ave Louisville, KY 40213 - United States Telephone: 502-467-8009 sales@caliberarmor.com NIJ STANDARD-0101.06 III and 0101.07 Draft RF2 Tested and verified to meet ballistic resistance as specified under NIJ Standard-0101.06 plus special threat tested to the new draft ballistic NIJ Standards of 0101.07 RF2

DISCLAIMEE

The information contained in this document is intended solely to provide general guidance. The right is reserved to make changes to this document without notice at any time. Nothing in this document (i) constitutes an offer, representation, warranty, term or condition or (ii) is a substitute for the need to employ adequate independent technical expertise and judgment.

EXPORT CONTROL ADVISORY
Model AR550 Is subject to the Export
Administration Regulations (EAR). It may not be
sold or otherwise provided to any non-U.S.
Person and/or exported or re-exported without a
valid U.S. Department of Commerce BIS Export
License, or applicable EAR license Exception.

QUALITY STANDARDS
Caliber Armor operates a documented quality
management system to ensure
the highest caliber armor available. Raw
materials are tested prior to production and
finished products are tested in credited ballistic
laboratories.